

**UNCLASSIFIED**

**AD 261 405**

*Reproduced  
by the*

**ARMED SERVICES TECHNICAL INFORMATION AGENCY  
ARLINGTON HALL STATION  
ARLINGTON 12, VIRGINIA**



**2050204157**

**UNCLASSIFIED**

**Best Available Copy**

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

USASRD L Technical Report 2196


PROPERTIES OF HOT-PRESSED BARIUM TITANATE

by


Arthur Brown

and

Robert Fischer



April 1961



U.S. ARMY SIGNAL RESEARCH AND DEVELOPMENT LABORATORY

FORT MONMOUTH, N. J.

April 1951

USASRDL Technical Report

PROPERTIES OF HOT-PRESSED BARIUM TITANATE

by

Arthur Brown

and

Robert Fischer

DA TASK NR. 3A99-15-001-01

U. S. ARMY SIGNAL RESEARCH AND DEVELOPMENT LABORATORY  
FORT MONMOUTH, NEW JERSEY

## CONTENTS

Abstract	
INTRODUCTION	1
METHOD	1
PROCEDURE	1
CHARACTERISTICS OF HOT-PRESSED BaTiO <sub>3</sub>	4
Density and Microstructure	4
Electrical Characteristics	4
CONCLUSIONS	10
ACKNOWLEDGMENTS	10
REFERENCES	10

## FIGURES

1. Hot-Pressing Apparatus	2
2. H. F. Coil and Die Assembly	3
3. Fractured Surface of Hot-Pressed BaTiO <sub>3</sub>	5
4. Fractured Surface of Kiln-Fired BaTiO <sub>3</sub>	6
5. Particle Replica of BaTiO <sub>3</sub> Powder	7
6. Dielectric Properties of Two Types of BaTiO <sub>3</sub>	15
7. Aging Properties of Two Types of BaTiO <sub>3</sub>	9

## PROPERTIES OF HOT-PRESSED BARIUM TITANATE

### INTRODUCTION

The objective of the program described was to develop a technique for producing a dense, hot-pressed barium titanate sample having an average grain size of less than one micron and to compare its electrical properties with those of conventionally-fired barium titanate.

Barium titanate had been hot-pressed by others using graphite dies. Hot-pressing it results in reduced barium titanate ceramic which, upon subsequent oxidation, was subject to grain growth. Hot-pressing of cadmium niobate in ceramic dies had previously been demonstrated at USASRD by DeBretteville, et al,<sup>1</sup> and barium titanate had been hot-pressed and some properties reported by Tennery.<sup>2</sup>

Further development of the hot-pressing technique has enabled the authors to produce nonreduced samples of extremely fine grain structure whose electrical properties are of interest.

### METHOD

The hot-pressing apparatus consists of an induction furnace used in conjunction with a die assembly. An over-all view of the assembled apparatus is shown in Figure 1.


The induction power supply is a 20-kw, 10-kc motor generator, which allows rapid heating with good control. The furnace, which was assembled on the platen of the press, was a refractory fire brick cut to fit inside the induction coil and around the die assembly. A manual, manually-operated hydraulic laboratory press was used. The furnace and die assembly are shown in Figure 2.

The ceramic dies which have proven most effective for our work with barium titanate 100%, stabilized zirconia made slightly porous to improve thermal shock resistance. Other materials such as alumina and alumina porcelains can also be used with some degree of success. A stainless steel bushing was shrunk onto the ceramic sleeve to serve as the susceptor and mechanical support.

The method used to prevent adherence of the material being pressed to the ceramic die consisted of embedding the sample in a relatively coarse zirconia powder (TAM No. 45006). This method prevented sticking to the die and allowed the sample to be ejected easily while hot. The amount of zirconia that diffused into the sample during firing has not been determined, but the layer of zirconia that adhered to the surface of the sample was easily removed by grinding.


### PROCEDURE

A sample disc of barium titanate 1/8 inch smaller in diameter than the zirconia die was preformed at 10,000 psi with no binder. This preformed disc was loaded into the hot-press in such a manner as to be completely encapsulated in zirconia placing sand. The loader was aligned in the induction coil, and a pressure of 5000 psi was applied and maintained out the heating cycle. The rate of heating was controlled in such a manner that a temperature of 2000° F was reached in ten minutes. The sample was held at this temperature and pressure twenty minutes and then quickly ejected from the die and buried in vermiculite to cool. After cooling, the sample was removed from its zirconia casing, ground to the desired shape, and polished.



M-58-315

FIG 1 HOT-PRESSING APPARATUS





Other combinations of pressure, time, and temperature of firing were investigated; however, pressures above 5000 psi lead to rapid deterioration of the dies, and a significantly lower temperature or shorter time does not yield a fully vitrified body.

## CHARACTERISTICS OF HOT-PRESSED $\text{BaTiO}_3$

### *Density and Microstructure*

The polished samples had a yellowish color that is characteristic of nonreduced barium titanate. Fractured surfaces were glassy, an indication of the high density and fine grain size. Density measurements, made by displacement, averaged 5.9 gm/cc, some samples measuring as high as 6.0 gm/cc. When examined under 500 X magnification, polished samples exhibited no apparent grain structure before or after etching.

After careful polishing, samples were etched in a solution of 0.5% HF and 1.0%  $\text{HNO}_3$ , and platinum shadowed carbon backed replicas were prepared and examined with the electron microscope at magnifications up to 20,000 X. It was found that due to the small grain size a satisfactory polishing and etching technique could not be developed.

Fractured surfaces were replicated and all electron micrographs are of unetched fractured surfaces. The grain size in the hot-pressed barium titanate was found to be less than 1 micron (Figure 2). Figure 4 illustrates the grain size observed in a fractogram of kiln-fired barium titanate.

The fine microstructure observed in the hot-pressed samples is attributed to the fine particle size of the starting material, and to the predominance of plastic flow as the mechanism of sintering under these conditions. The average particle size of the barium titanate used (TAM I T grade) was 0.5 micron. These particles were found to be agglomerated in such a manner that they indicated a particle size distribution of 1 to 5 microns by sedimentation methods. Electron micrographs showed the actual particles to be 1 micron and less (see Figure 5), essentially the same size as those appearing in the hot-pressed samples.<sup>8</sup> This indicates that there was no significant grain growth during densification and that hot-pressing offers a method to be used to control grain size.

### *Electrical Characteristics*

The electrical properties of hot-pressed barium titanate samples prepared as above were quite striking when compared to those of conventionally prepared samples. The dielectric strength has been found to be 500 volts per mil as compared with values of 100 to 200 volts per mil, usually observed in conventionally processed barium titanate samples 1/16 inch thick.

Figure 6 illustrates the differences observed in measurements of the dielectric constant and dissipation factor with temperature. The reduction in the peak of the dielectric constant in the vicinity of the Curie temperature is attributed to the fine grain size. At room temperature the dielectric constant is above 4000 and is independent of the orientation of the sample with respect to the direction of the former pressure. No dependence of K on frequency was found from 100 cps to 10 mc. Figure 7 depicts the variation of dielectric constant with time under static room temperature conditions for conventional and hot-pressed  $\text{BaTiO}_3$ . The samples were deaged by heating to 200°C for 2 minutes; aging time was measured from the moment of removal from the oven. Since the aging of the dielectric constant has been reported to be due to a gradual reorientation of the ferroelectric domains, the results of this test suggest that the domains in the hot-pressed material were relatively stable.<sup>9,10</sup> The long-term stability has not been studied in conventional K<sub>1</sub> bodies.




FIG 3 FRACTURED SURFACE OF HOT-  
PRESSED  $\text{BaTiO}_3$



FIG 4 FRACTURD SURFACE OF KILN-  
FIRED BaTiO<sub>3</sub>




FIG 5 PARTICLE REPLICA OF  $\text{BaTiO}_3$   
POWDER





FIG 6

DIELECTRIC PROPERTIES OF TWO TYPES OF BARIUM TITANATE



An attempt was made to pole hot-pressed samples of  $\text{BaTiO}_3$  by applying a high DC field at room temperature or while cooling from  $120^\circ\text{C}$ , but little or no piezoelectric response was observed.

### CONCLUSIONS

The hot-pressing technique described in this report produced a dense, nonreduced barium titanate sample with no apparent grain growth. The limiting factor in producing a fine-grained  $\text{BaTiO}_3$  body was in the particle size of the raw materials. A project has been initiated to produce a  $\text{BaTiO}_3$  powder with an average particle size of less than 0.1 micron.

The dielectric properties of these materials were greatly enhanced by small crystallite size, but the piezoelectric response was almost completely eliminated. These results show the significance of the effect of density and grain size on the ferroelectric properties of barium titanate and indicate that an extension of this study over a wider range of particle sizes, particularly below 0.1 micron, might be expected to produce new or improved electrical properties in ferroelectric materials.

### ACKNOWLEDGMENTS

The authors are grateful to John Charlton and Anne Dunlap of the Inorganic Dielectrics Team for compiling all the electrical measurements; to Sam DiVita and Ronald Brandmayr of the Inorganic Dielectrics Team and Nelson Terhune, former Chief of the Inorganic Dielectrics Team, for their guidance and assistance in preparing this report; and to Charles Cook, Jr., of the Exploratory Research Division "E" for the instructions in electron microscopy.

### REFERENCES

1. DeBretteville, Halden, and Vasilos, "Dielectric Studies in the System  $\text{CdO-Nb}_2\text{O}_5$ ," *Journal of the American Ceramic Society*, Vol. 40, Nr. 3, pp 56-59 (1957).
2. Tennery and Venerus, "Hot Pressing of Barium Titanate," Reported at 59th Annual Meeting of the American Ceramic Society, May 1957, Dallas Texas.
3. Leonhart, Cook, and Anderson, "Full and Partial Particle Replication for Electron Microscopy," *The Review of Scientific Instruments*, Vol. 31, Nr. 11, pp 1151-1155, Nov. 1960.
4. K. W. Plessner, "Aging of the Dielectric Properties of Barium Titanate Ceramic," *Proc. Phys. Soc.*, Vol. 69B, Part 12, p 1261 (1956).
5. McQuarrie and Buessem, "Aging in Barium Titanate," *Ceramic Bulletin*, Vol. 34, Nr. 12, p 102 (1955).
6. U. S. Pat. Nr. 2,990,602.

DISTRIBUTION LIST

Chief Signal Officer  
ATTN: SIGRD-4-A  
Department of the Army  
Washington 25, D. C.

Chief Signal Officer  
ATTN: SIGPD-851  
Department of the Army  
Washington 25, D. C.

Office of the Assistant Secretary of  
Defense (Research and Engineering)  
ATTN: Technical Library  
Room 3E1065, The Pentagon  
Washington 25, D. C.

Chief of Research and Development  
Department of the Army  
Washington 25, D. C.

Commanding General  
U. S. Army Electronic Proving Ground  
ATTN: Technical Library  
Fort Huachuca, Arizona

Commanding Officer  
U. S. Army Signal Missile Support Agency  
ATTN: SIGMS-AJ  
White Sands Missile Range  
New Mexico

Commanding Officer  
U. S. Army Signal Materiel Support Agency  
ATTN: USASMSA ADJ  
Fort Monmouth, New Jersey

Commander  
Rome Air Development Center  
ATTN: RCOIL-2  
Griffiss Air Force Base  
New York

Commanding General  
Hq. Ground Electronics Engineering Installations Agency  
ATTN: ROZMS  
Griffiss Air Force Base  
New York



# DISTRIBUTION LIST (Contd)

*Nr. Copies*

Commander Wright Air Development Division ATTN: WWAD Library Wright-Patterson Air Force Base Ohio	1
Commander U. S. Air Force Security Service ATTN: Directorate of Systems Engineering (ESD) DCS Communications-Electronics San Antonio, Texas	1
Chief of Naval Research ATTN: Code 427 Department of the Navy Washington 25, D. C.	1
Bureau of Ships Technical Library ATTN: Code 312 Main Nav. Building, Room 1528 Washington 25, D. C.	1
Director, Code 2027 U. S. Naval Research Laboratory Washington 25, D. C.	1
Commanding Officer & Director ATTN: Library U. S. Navy Electronics Laboratory San Diego 52, California	1
Director ATTN: Technical Documents Center U. S. Army Engineer Research & Development Laboratories Fort Belvoir, Virginia	1
Signal Corps Liaison Officer ATTN: Code 1071 Naval Research Laboratory Washington 25, D. C.	1
Signal Corps Liaison Officer Massachusetts Institute of Technology Building 26, Room 131 77 Massachusetts Ave. Cambridge 39, Massachusetts	1

# DISTRIBUTION LIST (Contd)

	<i>Nr. Copie</i>
U. S. Army Signal Liaison Officer Wright Air Development Division ATTN: WWOL-9 Building 50, Room 025 Wright-Patterson Air Force Base Ohio	1
Signal Corps Liaison Officer Lincoln Laboratory P. O. 73 Lexington, Massachusetts	1
Signal Corps Liaison Officer Rome Air Development Center ATTN: RCCL Griffiss Air Force Base New York	1
USASRDL Liaison Officer Hq., U. S. Continental Army Command Fort Monroe, Virginia	1
USASMSA Liaison Engineer Signal Section, Eighth U. S. Army A.P.O. 301 San Francisco, California	1
Chief Scientist, SIGRA SL-CS Room 3C124 USASRDL	1
USASMSA Liaison Office, SIGRA SL-LNW Room 4D117 USASRDL	1
U. S. Navy Electronics Liaison Office, SIGRA SL-LNS Room 4D119 USASRDL	1
Chief, United States Army Security Agency ATTN: ACofS, G4 (Technical Library) Arlington Hall Station, Arlington 12, Virginia	1
Directorate of Intelligence, Headquarters, United States Air Force ATTN: AFGIN-1b1 Washington 25, D. C.	2

# DISTRIBUTION LIST (Contd)

*No. Copies*

Commander-in-Chief  
Strategic Air Command  
ATTN: DOCER  
Offutt Air Force Base,  
Nebraska

1

Commander  
Air Proving Ground Center  
ATTN: Adj Technical Reports Branch  
Eglin Air Force Base  
Florida

1

Commander  
Air Force Cambridge Research Laboratories  
ATTN: CRO  
Laurence G. Hanscom  
Bedford, Mass.

1

Commander  
Air Force Command & Control Development Division  
ATTN: CCRR & CCSD  
Laurence G. Hanscom Field  
Bedford, Mass.

2

ARDC Liaison Office  
Naval Air Research & Development Activities Command  
Johnsville, Pa.

1

Chief, Bureau of Ships  
ATTN: Code 454  
Department of the Navy  
Washington 25, D. C.

1

Commander  
U. S. Naval Ordnance Laboratory, White Oak  
Silver Spring 19, Maryland

1

Commanding Officer  
ATTN: Technical Library, Building 330  
U. S. Army Chemical Warfare Laboratories  
Army Chemical Center  
Maryland

1

Signal Corps Liaison Officer  
Ordnance Tank Automotive Command  
U. S. Army Ordnance Arsenal  
Detroit Center Line, Michigan

1

# DISTRIBUTION LIST (Contd)

	Nr. Cc
Corps of Engineers Liaison Officer, SIGRA SL-LNE, USASRDL	1
Marine Corps Liaison Officer, SIGRA SL-LNR, USASRDL	1
U. S. CONARC Liaison Officer, SIGRA SL-LNF, USASRDL	2
Commanding Officer U. S. Army Signal Research Activity Evans Area	1
Chief, West Coast Office U. S. Army Signal Research & Development Laboratory Building 12 75 South Grand Avenue Pasadena 2, California	1
Chief Technical Information Division Hq., USASRDL	6
USASRDL Technical Documents Center Evans Area	1
Mail & File Unit Nr. 1	1
Materials Branch, EP&M Division	120
Commander Armed Services Technical Information Agency ATTN: TIPCR Arlington Hall Station Arlington 12, Virginia	10

AD _____ Div. _____	UNCLASSIFIED	AD _____ Div. _____	UNCLASSIFIED
U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C	U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C
A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED	A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED
AD _____ Div. _____	UNCLASSIFIED	AD _____ Div. _____	UNCLASSIFIED
U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C	U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C
A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED	A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED
AD _____ Div. _____	UNCLASSIFIED	AD _____ Div. _____	UNCLASSIFIED
U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C	U. S. Army Signal Research and Development Laboratory, Fort Monmouth, N. J. PROPERTIES OF HOT-PRESSED BARIUM TITANATE by Arthur Brown and Robert Fischer, USAFDEL Technical Report 2196, April 61, 10 pp incl. figures (DA Task 3A92-15-001-C)	1. Barium Titanate 2. Hot-Pressing 3. Fine Grain Structure  I. Brown, Arthur and Fischer, Robert II. U. S. Army Signal Research & Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A92-15-001-C
A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED	A technique for hot-pressing dense, sintered, fine-grained barium titanate is described, and the electrical properties of this body are compared with the properties of air-fired barium titanate.	UNCLASSIFIED